

# AdvanSix Inc. Capran<sup>®</sup> HS6262

Capran<sup>®</sup> HS6262 is a blue tinted heat stabilized cast film produced from modified nylon resin. It is recommended as a bagging film for advanced composite fabrication and other high temperature applications where softness and workability are essential. Capran<sup>®</sup> HS6262 has excellent heat stability and resistance to pin-holing. Capran<sup>®</sup> HS6262 is available in sheet in widths ranging from 54" to 80".

Product Specifications		
Thickness (ASTM D6988)		Yield (calculated)
Average	Single Point Minimum	
2.00 mils (50.8 microns) ± 12%	1.70 mils (43.2 microns)	12,217 in <sup>2</sup> /lb (17.4 m <sup>2</sup> /kg) ± 12%
3.00 mils (76.2 microns) ± 12%	2.55 mils (64.8 microns)	8,144 in <sup>2</sup> /lb (11.6 m <sup>2</sup> /kg) ± 12%

Properties at 73°F(23°C) - 50%RH	Typical Value		Test Method
	English	Metric	
The properties presented in this data table are typical values and are not to be interpreted as product specifications.			
Tensile Strength @ break	15,000 psi	103 MPa	ASTM D882
Elongation @ break	375%		ASTM D882
Modulus, Secant	80,000 psi	552 MPa	ASTM D882
Melting Point	495°F	257°C	DSC
Maximum Recommended Use Temperature <sup>(1)</sup>	450°F	232°C	-----

Capran<sup>®</sup> HS6262, like all nylon films, is a hydrophilic or water-sensitive material. Moisture and water act as plasticizers. The higher the moisture content of the film, the more flexible it becomes. The lower the plasticizer content, the stiffer it becomes. The level of moisture content at time of use is an important factor for successful performance.

NOTE: (1) The maximum recommended use temperature is a function of the duration at maximum temperature and is process specific.

## Contact AdvanSix

To learn more about the benefits of Capran<sup>®</sup> films, visit [Advan6.com](http://Advan6.com) or [Capran.com](http://Capran.com) or call: **1-844-890-8949** (toll free, U.S./Can.) **+1-973-455-3000** (international)

**AdvanSix**  
115 Tabor Road  
Morris Plains, NJ 07950



Capran is a registered trademark of AdvanSix Inc.  
September 2016, Printed in U.S.A.  
©2016 AdvanSix Inc. All rights reserved.

**ADVANSIX**