

AdvanSix Inc. Capran® 1500M

CAPRAN® 1500M is a 0.59 mil (15 micron) biaxially oriented nylon 6 film with a polymeric coating that enhances adhesion to a variety of printing inks, coatings, and adhesives. "M" coated products are also excellent for metallization processes.

Product Quality Specifications	Target		Test Method	Tolerance
	English	Metric		
Average Thickness	0.590 mil	15 microns	-----	± 5%
Basis Weight	10.588 lbs/ream	17.24 g/m ²	calculated	± 5%
Yield	40,800 in ² /lb	58.02 m ² /kg	calculated	± 5%
Dimensional Stability, TD	1.0 %		5 mins @ 160°C	2.5% max
Dimensional Stability, MD	2.0%			3.0% max
Haze	2.5%		ASTM D1003	4.0% max
Surface Tension, coated side	58 dynes/cm		ASTM D2578	56 dynes/cm min

Properties at 73°F(23°C) - 50%RH	Typical Value		Test Method	
	English	Metric		
The properties presented in this data table are typical values and are not to be interpreted as product specifications.				
Tensile Strength @ break	MD TD	34,000-42,000 psi 34,000-42,000 psi	234-290 MPa 234-290 MPa	ASTM D882
Elongation @ break	MD TD	70-90% 70-90%		ASTM D882
Modulus, Secant	MD TD	250,000-350,000 psi 250,000-350,000 psi	1724-2413 MPa 1724-2413 MPa	ASTM D882
Tear Strength, Graves	MD TD	1000-1500 gf/mil 1000-1500 gf/mil		ASTM D1004
Coefficient of Friction, Kinetic Coated to Film Film to Stainless Steel		0.60-0.90 0.20-0.30		ASTM D1894
Surface Tension, untreated side		> 50 dynes/cm		ASTM D2578
Oxygen Transmission Rate @77°F (25°C) / 0%RH		3.0-4.0 cc/100in ² /day	47-62 cc/m ² /day	ASTM D3985
Water Vapor Transmission Rate @100°F(37.8°C) / 100%H		20-23 gms/100in ² /day	310-357 gms/m ² /day	ASTM F1249

Contact AdvanSix

To learn more about the benefits of Capran® films, visit Advan6.com or Capran.com or call: **1-844-890-8949** (toll free, U.S./Can.) **+1-973-455-3000** (international)

Although AdvanSix Inc. believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute any representation or warranty of AdvanSix Inc., either expressed or implied. A number of factors may affect the performance of any products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein.

AdvanSix
115 Tabor Road
Morris Plains, NJ 07950



Capran is a registered trademark of AdvanSix Inc.
September 2016, Printed in U.S.A.
©2016 AdvanSix Inc. All rights reserved.

ADVANSIX