

## Product Specification

March 2014

<b>Product</b>	<b>Aegis® H85QP</b>
<b>Product Description</b>	Aegis® H85QP is a lubricated, medium viscosity nylon 6 extrusion grade homopolymer for cast or blown film. It conforms to FDA requirements of 21 CFR 177.1500 as well as EU Directive 2002/72/EC. It possesses the combination of strength, toughness and thermoforming properties associated with nylon 6 as well as excellent heat, chemical, and abrasion resistance.

## Typical Properties

	ASTM Test Method	Dry	Conditioned
<b>VISCOSITY</b>			
FAV	D-789	85	-
%96 SAV		3.19	
Melt Flow Rate (235/1.0) (g/10 min)	D-1238	3.5	-
<b>GAS BARRIER At 23 °C (73 °F)/0% RH</b>			
Oxygen Permeability, cc/m <sup>2</sup> /day (cc/100in <sup>2</sup> /day)		40.3 (2.600)	-
Nitrogen Permeability, cc/m <sup>2</sup> /day (cc/100in <sup>2</sup> /day)		14.0 (0.903)	-
Carbon Dioxide Permeability, cc/m <sup>2</sup> /day (cc/100in <sup>2</sup> /day)		72.8 (4.697)	-
<b>MOISTURE</b>			
Moisture Content, %		max. 0.08	
Extractable Content, %		max. 0.6	
Water Absorption in 24 hrs, %		1.6	
Equilibrium Moisture @ 50% RH, %		2.7	
Saturation Moisture Content, %		9.5	
<b>SPECIFIC GRAVITY (TYPICAL)</b>			
Specific Gravity	D-1505	1.13	-
<b>THERMAL</b>			
Melting Point, °C (°F)	D-3418	220 (428)	-

## Processing Guidelines

## Processing Guidelines

### Melt Viscosity vs Temperature

Melt Temperature 220 °C (428 °F)

The melt temperature range is 232 °C (450 °F) to 271 °C (520 °F).

Two factors affect the melt viscosity (stiffness or fluidity of the melt).

1. Mw of the resin. Higher Mw resin will have a higher melt viscosity than lower Mw resin.
2. Temperature of the melt. For any given Mw resin, higher process temperature will provide a more fluid melt viscosity than lower process temperatures.

### Typical Barrel Profile for Cast Films

Barrel 230-260 °C (446-500 °F)

Adapter 260-266 °C (500-510 °F)

Die 260 °C (500 °F)

Process Melt Temperature 260-270 °C (500-518 °F)

### Typical Barrel Profile for Tubular (Blown) Films

Barrel 246-254 °C (474-490 °F)

Adapter 260 °C (500 °F)

Die 254 °C (490 °F)

Process Melt Temperature 254-260 °C (490-500 °F)

### Screw Parameters

Metering Section 40%

Transition Section 3 to 4 flights

Feed Section balance of screw length

Compression Ratio 3.5:1 to 4.0:1 L/D Ratio 24:1

### Metering Section Flight Depth:

Screw Diameter	Recommended Depth
1"	0.055"
1.5"	0.060"
2"	0.070"
2.5"	0.080"
3.5"	0.100"
4.5"	0.115"
6"	0.135"

These values are for natural color resins only. Colorants or other additives may alter some or all of these properties. The data listed here fall within the normal range of product properties, but should not be used to establish specification limits nor used alone as the basis of design.

### Contact AdvanSix

To learn more about the benefits of Aegis® Nylon Resins, visit

[Advan6.com](http://Advan6.com) or call:

**1-844-890-8949** (toll free, U.S./Can.)

**+1-973-455-3000** (international)

Although AdvanSix Inc. believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute any representation or warranty of AdvanSix Inc., either expressed or implied. A number of factors may affect the performance of any products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein.

### AdvanSix

115 Tabor Road  
Morris Plains, NJ 07950



Aegis is a registered trademark of AdvanSix Inc.  
September 2016, Printed in U.S.A.  
©2016 AdvanSix Inc. All rights reserved.